



# Data Sheet

## 3/4" CLASS II PERMEABLE AGGREGATE BASE



### Gradation

SIEVE SIZE	PERCENT PASSING	CALTRANS SECTION 26
1"	100	100
3/4"	98	90 - 100
1/2"	84	
3/8"	74	40 - 100
#4	35	25 - 40
#8	22	18 - 33
#30	10	5 - 15
#50	7	0 - 7
#200	3.5	0 - 3



## Physical

TEST NAME	RESULT	REQUIREMENTS
Durability Index CTM 229	45	40 minimum
Sand Equivalent CTM 217	75	75 minimum

All listed data is provided by the aggregate producer. North Bay Materials does not perform or offer in-house aggregate testing.

### **Disclaimer – Aggregate Material Limitations and Liability:**

Please note: Due to natural shifting and separation that can happen during transportation, aggregate gradations are only guaranteed at the producer's facility—not at the jobsite. North Bay Materials and our suppliers make no claims or guarantees that this material will meet specific project requirements, specifications, or design standards. It is the buyer's responsibility to confirm suitability and obtain any necessary approvals or certifications prior to use. All materials are provided as *is*, with no warranties—express or implied—including but not limited to warranties of merchantability or fitness for a particular purpose. We do not guarantee how the material will perform once installed or in any finished work. By purchasing, the buyer agrees that North Bay Materials and our suppliers are not liable for any damages—including indirect, incidental, special, or consequential losses such as lost profits—whether based on warranty, contract, negligence, or any other legal theory, even if those damages were foreseeable.



North Bay Materials

707 940 9419

[nbm@NorthBayMaterials.com](mailto:nbm@NorthBayMaterials.com)

[www.NorthBayMaterials.com](http://www.NorthBayMaterials.com)